

Material: P1288

Color: Natural

Package: Bag

Quantity: 25kgs

PRODUCTION DATE: 8th April. 2025

Mechanical Properties	dry/cond	Test Standard	Unit	Value
Stress at Break (1A;50mm/min)	dry	ISO 527	MPa	164
Tensile Modulus (1A;50mm/min)	dry	ISO 527	MPa	1172
Flexural Modulus (10mm/min)	dry	ISO 178	MPa	7358
Flexural Strength (10mm/min)	dry	ISO 178	MPa	241
Izod notched Impact Strength (23°C;50%RH)	dry	ISO 180/1A	kJ/m ²	18.1
Izod Unnotched Impact Strength (23°C;50%RH)	dry	ISO 180/1U	kJ/m ²	-
Thermal Properties	dry/cond	Test Standard	Unit	Value
Melting point (10°C/min)	dry	ISO 11357-1/-3	°C	-
Temperature of Deflection Under Load (1.80MPa)	dry	ISO 75-1/-2	°C	-
Other Properties	dry/cond	Test Standard	Unit	Value
Density	dry	ISO 1183-1	g/cm ³	-
Ash Content	dry	ISO 3451-1	%	31

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a formal commitment or warranty on our part.

Report Date: 10th April. 2025